

PRODUCT DATA SHEET

ANLEGGSEMENT

CEM I 52,5N

LATEST REVISION MARCH 2023

The cement satisfies the requirements according to NS-EN 197-1:2011 for Portland cement CEM I 52,5 N. In addition, the cement satisfies the requirements for DS/INF 135:2020 Classification of cement, classification (LA) and (MS).

Certificate-DOP no. 1111-CPR-0413

DOP no. 1111-DoP-NO11-0413

Dancert certificate no. 484

Properties		Declared values	Requirements in NS-EN 197-1:2011	Requirements in DS/INF 135:2020
Fineness(Blaine m ² /kg)		415		
Specific weight (kg/dm ³)		3.14		
Soundness (mm)		1	≤10	
Initial setting time (min)		120	≥45	
Compressive strenght (MPa)	1 day	21		
	2 days	33	≥20	
	7 days	49		
	28 days	63	≥52.5	
Sulfate (% SO ₃)		≤4.0	≤4.0	
Cloride (% Cl ⁻)		≤0.07 *	≤0.10	*Danish additional req.
Water soluble chromium (ppm Cr ⁶⁺)		≤2	≤2 ¹⁾	
Alkalis (% Na ₂ O _{ekv})		≤0.6		≤0.6
Loss on ignition (%)		≤5.0	≤5.0	
Insoluble residue		≤5.0	≤5.0	
C ₃ A (%)		≤8		≤8
Clinker (%)		96	95-100	
Minor additional constituents (%)		4	0-5	

1) According to EU-regulation REACH Annex XVII point 47 Chromium VI-compounds



Heidelberg Materials Sement Norge AS
PO.box 143, Lilleaker, NO-0216 Oslo

www.sement.heidelbergmaterials.no